

Test Report SL52025233395801TX Date:May 29,2020 Page 1 of 2

SHANGHAI XM GROUP LTD

ROOM 2403, ZHONGYI INTERNATIONAL BUILDING NO.1833, NORTH ZHONGSHAN ROAD, SHANGHAI

The following sample(s) was/were submitted and identified on behalf of the client as:

Sample Description : (A)Woven fabric (Gefest-420,100% cotton, 420gsm, satin 4/1, Roll #43, Order:

FRL-156-WD-17-XMG-037-msk)

Sample Color : (A)Black

Proposed Care Instruction:

Sample Receiving Date : Mar 25, 2020

Testing Period : Mar 25, 2020 - May 29, 2020

Test Result(s) : Unless otherwise stated the results shown in this test report refer only to the

sample(s) tested, for further details, please refer to the following page(s).

Test Performed : Selected test(s) as requested by applicant

Signed for and on behalf of

SGS-CSTC Standards Technical Services (Shanghai) Co., Ltd Testing Center

Hattie Chen (Account Executive)



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions of Electronic Documents at <a href="http://www.sgs.com/en/Terms-and-Conditions/Terms-and-Condi

3^{**}Building,No.889,Yishan Road,Xuhui District Shanghai,China 200233 中国・上海・徐汇区宜山路889号3号楼 邮编: 200233 t (86-21) 61402666 t (86-21) 61402666

f (86-21) 64958763 f (86-21) 64958763 www.sgsgroup.com.cn e sgs.china@sgs.com



Test Report

SL52025233395801TX

Date:May 29,2020

Page 2 of 2

Test Result

Summary of Test Results						
Test Method	Test Name	Status / Performance Level				
DC EN ICO 44642, 2045	Protective clothing – Clothing to protect against heat and flame					
BS EN ISO 11612: 2015	Molten Iron splash (Code letter E)	Performance Level 3				

BS EN ISO 11612: 2015 Protective clothing - Clothing to protect against heat and flame*

Clause &Test Name	Test Method	BS EN 11612: 2015 Requirements		Results Obtai	ned	Level/ Status
7.5 Molten Iron splash (Code letter E)	ISO 9185	Molten Iron splash (g) Performance Levels Min Max E1 60 < 120 E2 120 < 200 E3 200	Specimen 1 Specimen 2 Specimen 3 Specimen 4	Mass (g) 201 202 203 201	Skin simulant) No Damaged No Damaged No Damaged No Damaged	Pass Level 3

After 5 washes

Wash procedure: ISO 6330:2012; Using horizontal axis, front-loading type machine; Procedure No.6N, Machine Wash At 60℃; with 2kg total dry mass (Type I (100% Cotton) Ballast+ Specimen), 'ECE(A)' detergent+ Sodium Perborate+ TAED, Tumble Dry Low, Less Than 60℃

*This test was carried out by SGS India lab

The statement of conformity in this test report is only based on measured values by the laboratory and does not take their uncertainties into consideration.

End of Report



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its Intervention only and within the limits of Client's Instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

3^{rt}Building,No.889,Yishan Road,Xuhui District Shanghai,China 200233 中国・上海・徐江区宜山路889号3号楼 邮编: 200233 t (86-21) 61402666 f (86-21) 64958763 t (86-21) 61402666 f (86-21) 64958763 www.sgsgroup.com.cn e sgs.china@sgs.com