

**Test Report** Page 1 of 2 No. SHSL1309231803TX Date: Oct 16, 2013

**XM TEXTILES** 

ROOM 2403, ZHONGYI INTERNATIONAL BUSINESS BUILDING NO.1833, NORTH ZHONGSHAN ROAD, PUTUO DISTRICT, SHANGHAI

The following sample(s) was/were submitted and identified on behalf of the client as:

Sample Description Woven fabric: Poseidon 79%cotton 20%polyester 1%antistatic 300gsm twill 2/2

FR, in dark navy Part FL-07

Proposed Care Instruction

**Test Performed** Selected test(s) as requested by applicant

Sample Receiving Date

Sep 22, 2013 **Testing Period** Sep 22, 2013 TO Oct 16, 2013

For further details, please refer to the following page(s). Test Result(s)

Signed for and on behalf of SGS-CSTC Ltd.

Tina Xi

Account Executive

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <a href="http://www.sgs.com/en/Terms-and-Conditions.aspx">http://www.sgs.com/en/Terms-and-Conditions.aspx</a> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <a href="http://www.sgs.com/en/Terms-and-Conditions/Terms-an

3<sup>rd</sup>Building,No.889,Yishan Road,Xuhui District Shanghai,China 200233 中国・上海・徐汇区宜山路889号3号楼 邮編: 200233 t (86-21) 61402666 f (86-21) 64958763 t (86-21) 61402666 f (86-21) 64958763

www.cn.sgs.com e sgs.china@sgs.com



**Test Report** 

No. SHSL1309231803TX

Date: Oct 16, 2013

Page 2 of 2

## **Test Result**

Protective clothing- clothing to protect against heat and flame

General requirements of limited flame spread(Ref. ISO 11612:2008 Clause 6.3/ ISO 15025:2000 procedure A)

## After 100 washes

	Material						A
Sample	Length wise		Width wise			Average	
Specimen	1	2	3	1	2	3	
The afterflame Time (second)	NIL	NIL	NIL	NIL	NIL	NIL	NIL
The afterglow Time(second)	NIL	NIL	NIL (	NIL	NIL	NIL	NIL
Flaming to the top or either side edge	N	N	N	N	N	N	1
Melt or suffer flaming or molten debris	N	N	N	N	N	N	/
Hole formation	N	N	N	N	N	N	/

Remarks: Flame application time: 10 seconds

Y-Yes N- No

## Requirements:

No specimen shall suffer flaming to the top or either side edge;

No specimen shall suffer hole formation;

No specimen shall melt or suffer flaming or molten debris;

The mean value of afterflame time shall be ≤2s;

The mean value of afterglow time shall be ≤2s;.

Type of ignition: Surface ignition(A1)

Washing conditions: (Ref . ISO 6330:2000/AMD 1:2008, Wash Program No.2A: Using front load, horizontal drum type machine, Machine Wash at 75 degree C with 2kg total dry mass (knitted polyester ballast+specimen), and 77%ECE(A)+3%TAED+20% sodium perborate tumble dry low).

\*\*\* End of Report \*\*\*

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <a href="http://www.sgs.com/en/Terms-and-Conditions.aspx">http://www.sgs.com/en/Terms-and-Conditions/Terms-and-Conditions/Terms-and-Conditions.aspx</a> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <a href="http://www.sgs.com/en/Terms-and-Conditions/Terms-an

3<sup>rd</sup>Building,No.889,Yishan Road,Xuhui District Shanghai,China 200233 中国・上海・徐汇区宜山路889号3号楼 邮编: 200233 t (86-21) 61402666 t (86-21) 61402666

f (86–21) 64958763 f (86–21) 64958763 www.cn.sgs.com e sgs.china@sgs.com